

ABSTRACT OF THE DISCLOSURE

Amolding composition comprising (A) a fibrous material,
(B) an inorganic filler, at least one of (C) a radical
5 polymerizable unsaturated polyester having an acid value of
3 to 60 KOHmg/g and (D) a radical polymerizable unsaturated
polyester-polyamide having an acid value of 3 to 60 KOHmg/g,
and (E) a radical generator, wherein component (B) has been
internally added to at least one of component (C) and component
10 (D) and a molding composition comprising (A) a fibrous material,
at least one of (C) a radical polymerizable unsaturated polyester
having an acid value of 3 to 60 KOHmg/g and (D) a radical
polymerizable unsaturated polyester-polyamide having an acid
value of 3 to 60 KOHmg/g, (E) a radical generator, and (F)
15 a di- or higher valent metal salt of a fatty acid.

09901662.07101
TOP 20 29910660